

				T min	T max	
HT	EZTRA 001 FFKM 75 BLACK MT				-15°	300°
	Color Black	Hardness 75 ShoreA	Rating High Temperature ++++	Rating Chemicals ++++		
	*Vulcanization: Triazine					
	*Improved performance and compression set at temperatures up to 300°C					
	*Not compatible with water, vapour and amine applications at high temperatures					
	EZTRA 002 FFKM 75 BLACK HT				-10°	320°
	Color Black	Hardness 75 ShoreA	Rating High Temperature +++++	Rating Chemicals ++++		
	*Vulcanization: Peroxide					
	*Excellent temperature resistance performance up to 320°C					
	*Good general chemical resistance				-5°	320°
	EZTRA 007 FFKM 80 BLACK HTZ					
	Color Black	Hardness 80 ShoreA	Rating High Temperature +++++	Rating Chemicals +++		
	*Vulcanization: Triazine					
*Excellent resistance to very high temperatures						
*Good chemical resistance, except for amines and high-temperature water and steam environments				-10°	300°	
EZTRA 011 FFKM 90 BLACK HT						
Color Black	Hardness 90 ShoreA	Rating High Temperature ++++	Rating Chemicals +++			
*Vulcanization: Peroxide						
*Excellent resistance to high temperatures together with good general chemical resistance						
*Excellent performance in high-pressure conditions						

FFKM at its biggest.

				T min	T max	
FB + M	EZTRA 003 FFKM 75 BLACK CHT FDA				-20°	275°
	Color Black	Hardness 75 ShoreA	Rating High Temperature +++	Rating Chemicals +++++		
	*Vulcanization: Peroxide					
	*Universal FFKM that best reconciles high-temperature resistance and performance in chemically aggressive environments					
	* Certified according to FDA cfr.21, 3-A Sanitary and USP Class VI				-10°	275°
	EZTRA 022 FFKM 75 WHITE HT FDA					
	Color White	Hardness 75 ShoreA	Rating High Temperature ++++	Rating Chemicals +++		
	*Vulcanization: Peroxide					
	*White FFKM for food applications with excellent resistance to high temperatures – Certified according to FDA cfr.21, 3-A Sanitary and USP Class VI				-20°	260°
	EZTRA 023 FFKM 75 WHITE CHT FDA					
Color White	Hardness 75 ShoreA	Rating High Temperature +++	Rating Chemicals +++++			
*Vulcanization: Peroxide						
*Specific material for food, medical and pharmaceutical applications with excellent chemical resistance - Certified according to FDA cfr.21, 3-A Sanitary and USP Class VI						

FFKM at its biggest.

				T min	T max	
LT	EZTRA 006 FFKM 75 BLACK LT				-42°	240°
	Color Black	Hardness 75 ShoreA	Rating High Temperature ++	Rating Chemicals ++++		
	*Vulcanization: Peroxide					
	*Specific for low-temperature applications down to -42°C					
*Combines an extended temperature range with excellent chemical resistance						
	EZTRA 013 FFKM 90 BLACK LT				-30°	220°
	Color Black	Hardness 90 ShoreA	Rating High Temperature ++	Rating Chemicals ++++		
	*Vulcanization: Peroxide					
	*FFKM special for applications where very good chemical resistance at low temperatures (down to -30°C) and high-pressure values are required					
	EZTRA 012 FFKM 90 BLACK ED				-5°	260°
	Color Black	Hardness 90 ShoreA	Rating High Temperature +++	Rating Chemicals +++++		
	*Vulcanization: Peroxide					
	*FFKM specific for Anti Explosive Decompression applications, certified according to Norsok M-710, NACE and API 6A					
*Excellent chemical and high-temperature resistance (up to 260°C)						

FFKM at its biggest.